

## Butyl Tin Stabilisers

Grade	Chemical Name	Appearance	Tin Content	Specific Gravity	Refractive Index	Applications
STS-1	Butyl Tin Mercaptide	Pale Yellow Liquid	15-16%	1.08-1.1	1.48-1.52	PVC Heat stabiliser for Soft films, Hoses, Tubings & Injection Mouldings
STS-1AM	Butyl Tin Mercaptide	Pale Yellow Liquid	18-18.5%	1.1 -1.13	1.48-1.49	PVC Heat stabiliser for Rigid/ Soft films, Hoses, Tubings, Injection Mouldings
STS-101	Di Butyl Tin Dilaurate	Pale Yellow Liquid	18-19%	1.045-1.065	1.45-1.46	Processing of Rigid & Plasticized PVC. Excellent light stabiliser
STS-102	Di Butyl Tin Maleate	Pale Yellow Liquid	16.5-17.5%	1.15-1.16	1.48-1.495	Stabilisers for PVC / ABS, excellent light stability