

Property	Grade PR-065	Grade PR-057
Appearance	White Powder	White Powder
K Value (1% Cyclohexanone)	64-67	57-60
Degree of Polymerisation (0.4% Nitrobenzene)	980-1080	620-720
Bulk Density (gm/ml)	0.46-0.54	0.46-0.54
Sieve Analysis (42 Mesh pass wt%)	99.9	99.9
Volatile Matter (wt% (105 C - 1hr)	0.3	0.3
Packing 25 Kgs Net HDPE Woven Sacks with LDPE Liner		